

Gaco

Coverage Rates

S4200

Products	Roof Types				
	Single-Ply	Metal**	Smooth Mod Bit or Smooth Built-Up	Granulated Cap Sheet	Concrete
GacoWash <i>Concentrated Cleaner</i>	9:1 ratio: 1 gallon concentrated equals 4000 sq. ft.	9:1 ratio: 1 gallon concentrated equals 4000 sq. ft.	N/A	N/A	9:1 ratio: 1 gallon concentrated equals 4000 sq. ft.
GacoFlex A4271 BleedTrap <i>Sealer for Asphalt Roofing</i>	N/A	N/A	1 coat at 100 sq. ft./gal 6-8 dry mils	1 coat at 100 sq. ft./gal 6-8 dry mils	N/A
GacoFlex E5320 <i>2-Part Epoxy Primer/Filler</i>	N/A	Rusty metal: 2 coats at 250 sq. ft./gal per coat	N/A	N/A	1 coat at 250 sq. ft./gal
GacoFlex SF4200 SeamSeal <i>Solvent-Free Silicone Sealant</i>	75-100 linear feet at 4" wide 32 mils thickness	450 fasteners or 75-100 linear feet at 4" wide 32 mils thickness	75-100 linear feet at 4" wide 32 mils thickness	75-100 linear feet at 4" wide 32 mils thickness	75-100 linear feet at 4" wide 32 mils thickness
GacoFlex S4200 Series <i>Solvent-Free 100% Silicone Roof Coating</i>	1 coat 10 year = 1.25 gal/sq. 15 year = 1.75 gal/sq. 20 year = 2.25 gal/sq.	1 coat 10 year = 1.25 gal/sq. 15 year = 1.75 gal/sq. 20 year = 2.25 gal/sq.	1 coat 10 year = 1.25 gal/sq. 15 year = 1.75 gal/sq. 20 year = 2.25 gal/sq.	1 coat 10 year = 1.75 gal/sq. 15 year = 2.25 gal/sq. 20 year = 2.75 gal/sq.	1 coat 10 year = 1.25 gal/sq. 15 year = 1.75 gal/sq. 20 year = 2.25 gal/sq.
GacoFlex S4200 Series <i>DFT Warranty</i>	10 year = 20 WFT/ 18 DFT 15 year = 28 WFT/ 26 DFT 20 year = 36 WFT/ 34 DFT	10 year = 20 WFT/ 18 DFT 15 year = 28 WFT/ 26 DFT 20 year = 36 WFT/ 34 DFT	10 year = 20 WFT/ 18 DFT 15 year = 28 WFT/ 26 DFT 20 year = 36 WFT/ 34 DFT	10 year = 28 WFT/ 26 DFT 15 year = 36 WFT/ 34 DFT 20 year = 44 WFT/ 42 DFT	10 year = 20 WFT/ 18 DFT 15 year = 28 WFT/ 26 DFT 20 year = 36 WFT/ 34 DFT
GacoFlex SF2036 WalkPad <i>Solvent-Free Silicone Walkway System</i>	4 gallons per square to achieve a 2' x 50' walkway Granules: 0.5 lb. per square	4 gallons per square to achieve a 2' x 50' walkway Granules: 0.5 lb. per square	4 gallons per square to achieve a 2' x 50' walkway Granules: 0.5 lb. per square	4 gallons per square to achieve a 2' x 50' walkway Granules: 0.5 lb. per square	4 gallons per square to achieve a 2' x 50' walkway Granules: 0.5 lb. per square

NOTE: Application rate is job specific. Additional material may be required due to overspray, wind, waste and residual coating left in the container.

**Add surface factor for metal roof profile, normally 15-40%.

†Additional coating may be required to achieve dry mil requirement due to surface profile.

GACOFLEX S4200 QUICKSPECS

Approved Substrates: EPDM, PVC, Hypalon, TPO, Metal, SBS, APP, BUR (smooth only), Spray Polyurethane Foam, Silicone Coatings, and Concrete.

Single-Ply

1. Repair Membrane
2. Clean roof with GacoWash
3. Prepare roof with SF4200 SeamSeal and GacoFlex 66S Reinforcing Polyester Mesh

BUR / Mod Bit

1. Repair Membrane
2. Apply GacoFlex A4271 BleedTrap Sealer
3. Prepare roof with SF4200 SeamSeal and GacoFlex 66S Reinforcing Polyester Mesh

*When using GacoFlex S20 or S2100 series in lieu of GacoFlex S4200, an application of GacoFlex E5320 2-part epoxy primer is required prior to S20/S2100 coating application.