

TECHNICAL INFORMATION SHEET

AC Catalyst Powder

Item Description

AC Catalyst Powder 3.5 oz (100 g)
 AC Catalyst Powder 10.6 oz (300 g)

Item Number

W70CFACP100G
 W70CFACP300G



Product Information

Description:

AC Catalyst Powder is a reactive agent, based on 50% dibenzoyl peroxide, used to induce setting of AC Primer and AC Fast FR. Use when additional catalyst is required.

Method of Application:

1. Mix resin with a spiral agitator until the liquid is a uniform color.
2. Add AC Catalyst Powder to resin and mix with the same agitator for 2 minutes or until the powder is completely mixed.
3. Review individual Technical Information Sheets for AC Primer and AC Fast FR for additional mixing instructions.

Storage:

- Always store in cool and dry location.
- **Do not store in direct sunlight** or in temperatures below 35 °F (1.7 °C) or above 80 °F (27 °C).
- Store separately from resin components.
- Appropriately discard of any AC Catalyst Powder that has clumped together.
- For best use, the material is to be acclimated at temperatures between 65 – 70 °F (18 – 21 °C) 24 hours before application.

Shelf Life:

Approximate shelf life is 36 months with proper storage.

Coverage Rate:

Refer to the Technical Information Sheet of the corresponding product to determine the quantity of catalyst powder to be added.

Clean-Up:

Cured AC Primer and AC Fast FR may be disposed of in standard landfills. This is accomplished by thoroughly mixing all components. **Note:** Uncured resin and catalyst are considered hazardous materials and must be handled as such, in accordance with local, state and federal regulations. Do not throw uncured resin or catalyst away.

Precautions:

- **CAUTION:** Product becomes **EXTREMELY HOT** while reacting, reaching approximately 230 °F (110 °C). It may spit, pop, and steam. Mix in metal containers. Do not mix on completed roof membrane.
- Refer to Safety Data Sheet (SDS).
- Prior to opening the containers, wear appropriate safety glasses and protect hands and wrists by wearing gloves.

LEED® Information:

Post-Consumer Recycled Content: 0%
 Post Industrial Recycled Content: 0%
 Manufacturing Location: China

*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.

Please contact Firestone Technical Services Department at 1-800-428-4511 for further information.

This sheet is meant to highlight Firestone products and specifications and is subject to change without notice. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications or other technical documents, subject to normal roof manufacturing tolerances. Neither Firestone nor its representatives practice architecture. Firestone offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Firestone accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Firestone representative is authorized to vary this disclaimer.